

# Earthen Construction, as a Solution to Building Industries In Ghana

Zakari Mustapha<sup>1</sup> and Akani Michael<sup>2</sup>

Department of Building Technology, School of Engineering, Cape Coast Polytechnic Cape Coast, Ghana.

[zakariyamustapha@yahoo.co.uk](mailto:zakariyamustapha@yahoo.co.uk)<sup>1</sup> and [makuskani@yahoo.com](mailto:makuskani@yahoo.com)<sup>2</sup>

## Abstract

Adequate shelter is a basic human need. The cost of housing delivery in Ghana has been on the increase, particularly for the poor. The use of sandcrete blocks as walling units have greatly influenced the construction industry in Ghana as compared to other building materials but sand as the main constituent of sandcrete is quite expensive as compared to laterite. Sand as the main constituent of sandcrete is quite expensive as compared to laterite but the latter forms about 70% of the land surface of the country and can equally be used for moulding blocks when combined with cement and could be comparably in performance with sandcrete blocks but less expensive than sand (Adam, 2004, Gooding and Thomas, 1995).

The purpose of the study was to determine the factor that has impact on the use of sustainable innovative building technologies for low-income residential buildings in the urban areas. The study also sought to compare the durability properties of walling units produced from the mixture of laterite and cement to that of sand and cement. A structured interview approach was adopted for the data collection. Architects, property developers – Ghana Real Estate Developers Association (GREDA), Social Security and National Insurance Trust (SSNIT) and the State Housing Company Ltd (SHC) were among the institutions that were interviewed. Laboratory tests were carried out on twelve blocks each moulded from different mix ratios of 1:6, 1:8, 1:10 for sandcrete blocks, and 1:10 for laterite blocks to determine the compressive strength, density, water absorption and total volume porosity after seven days and twenty eight days respectively.

It was found out that residential building industries have stopped using earth material for construction but have high expectation on the success of the new building technology if introduced into the market. The results of the laboratory experiment were given in the text. It was concluded that sandcrete blocks were more durable than laterite blocks but the latter can equally be used as a walling unit to assist in the solving of the housing problems in the country.

## Keywords:

Durability, sandcrete blocks, laterite blocks, low-income housing, Ghana

## Introduction

Ghanaians have been facing serious housing problems, particularly for the poor who make up the majority of the total population of twenty- three million eight hundred and thirty seven thousand (23,837,000) ([www.myjoyonline.com](http://www.myjoyonline.com)). Affordability is one of the problems faced by housing

finance institutions in Africa. It was estimated that an accumulated housing deficit of Ghana was 1,000,000 and about 130,000 housing units should be built annually in addition to the 25,000 to 40,000 units the citizens are providing currently ([www.theghanaijournal.com](http://www.theghanaijournal.com)). The National Housing Policy by the Ministry of Works and Housing, Ghana, in 1986 emphasized the development and use of local building materials to contribute to the solution of the housing crisis and to reduce the importation of foreign building materials to a minimum as indicated by the National Housing Policy (Gidigas, 2005).

This research considered the construction industry and building technologies in use for residential buildings in Ghana, and on the potential to put this industry into contact with innovative building technologies and changes which have taken place in the construction industry elsewhere in the country. The significant proportion of population increases in the developing countries have been absorbed by urban areas i.e. 83% in 2000-10. Urban settlements in developing countries are at present growing five times as fast as those in the developed countries. Also Ghana becomes more and more urbanized (Karl, 2000). Shelter conditions in many developing countries have deteriorated steadily over the last 50 years while the privileged few have access to better housing, the vast majority however, continue to live in sub standard conditions. (Patara, 1998). To alleviate their problems, the construction industries have to improve their production output (Karima, 1998). In a number of countries – both industrialized as well as developing countries- the construction industry has succeeded in improving its performance and in the alleviation of at least a part of the housing problems in urban areas by developing and applying innovative building technologies based on locally available resources, that can be sustained economically and ecologically. Laterite has been used in construction of shelter from time immemorial and approximately 30% of world's present population still lives in laterite structures. Due to its wide application, the cost of sandcrete block has been gradually increased which has affected the overall cost of the housing delivery in the country. Their wide spread use can be attributed to their relative cost advantage, easiness to obtain and satisfactory durability characteristics (Andam, 2004; Gooding and Thomas, 1995). Thus, it is important to find alternative local materials for block production which could be comparable in performance but less expensive than sand to reduce the cost of walling in housing construction in Ghana. The search for these alternative materials may require methods of combining various existing ones, including sand to come out with new composite materials (Dorcas, 2006). A mixture of laterite and cement for block production may be the efficient way of achieving the cost reduction. Laterite is an extra-ordinary material and it can be found in all parts of Ghana. About 70 percent of the land surface of Ghana is covered by laterite, as stated by (Gidigas, 2005). Laterite is cheap, environmentally friendly and abundantly available building material in the tropical region (Fales, 1991). The research was limited to low-income households in the urban areas because the demand for housing is currently high at the major cities of Ghana namely, Accra, Tema and

Kumasi. It has been established that durability of a cement- based material is influenced by physio- chemical agents. This research however focused mainly on the physical aspects of durability such as the bulk properties. These properties of the two materials under consideration (sandcrete and Landcrete blocks) were compared and conclusions drawn in the ensuing chapters.

## **Statement of the problem**

There is rapid population growth in the urban areas. This situation has led to high demand on residential buildings. The problematic housing situation in Ghana- alike in many developing countries- has been attributed to the rapid urban growth and the non-performance of the construction industry in the housing sector to meet the demand for housing (Government of Ghana, 2000). A major contributing factor to the housing problems is the inadequate application of technologies and use of natural resources (UNCHS, 1991). Only very wealthy Ghanaians and the international community in Ghana can afford to buy a house in the urban core ([www.Ghanaweb.com](http://www.Ghanaweb.com)). The urge to find alternative materials to existing conventional ones and the need to bring down the cost of construction has compelled the researchers to intensify work on laterite with a view to investigating its usefulness wholly as a construction material or partly as a substitute for fine aggregate component of sandcrete. It is therefore important to fully explore and utilize all available local building materials as well as possible production of materials for construction from our industrial and agricultural wastes. Doing this, it is necessary to examine possibilities of introducing the use of our local material such as laterite which will assist in construction of low-cost housing, yet more durable buildings to that of sandcrete blocks.

## **Purpose of the study**

The study compared the durability properties of the walling units produced from the mixture of laterite and cement to that of sand and cement building blocks and its possible application for low-income housing in the urban areas.

The specific objectives for the study are as follows:

- To find out the compressive strengths (CS) of the various blocks.
- To find out their bulk dry densities (BDD) and total water absorption (TWA).
- To establish the total volume porosities (TVP).
- To find out the circumstances under which innovative building products/technologies are transferred in the building industry

## **Research questions**

Sandcrete blocks are widely used in Ghana as a walling unit. To reduce cost and encourage the use of our local material such as laterite, which can be obtained at or close to every construction

site in Ghana to serve as an alternative material for block production. However, the questions that arise are:

- What prevents the use of innovative building technologies for low-income housing?
- What are the characteristics of residential building industry?
- What are the compressive strengths of sandcrete and landcrete blocks?
- What are their bulk dry densities and total water absorptions?
- What are their total volume porosities?

### **Significance of the study**

The relative advantages of laterite over sandcrete blocks in terms of durability for low-income housing will be known. This will reduce the over-dependence of housing construction with sandcrete blocks and encourages the use of less expensive materials such as laterite

### **Research Methodology**

The researcher examined how and under what circumstances residential housing innovations become standard industry practices. Architects, property developers – Ghana Real Estate Developers Association (GREDA), Social Security and National Insurance Trust (SSNIT) and the State Housing Company Ltd (SHC) were among the institutions that were interviewed. Representatives of Building and Road Research Institute (BRRI) at the Centre for Scientific Research Institute (CSRI) were also interviewed. Laboratory experiments were carried out on sand and laterite with four different mix ratios of 1:6, 1:8 and 1:10 of landcrete (cement: laterite) blocks of sizes of 450mm× 225mm× 150mm were moulded, making twelve (12) in number for each ratio and was compared with twelve (12) number cement: aggregate ratio of 1:10 as specified by the Ghana Standard Contract Document. Hence the total sample was forty-Eight (48). To ensure the validity of the study, the sampling procedure used in this research was census, since all the ratios in the population of interest were worked on. Data were analyzed by categorizing them in an orderly manner in terms of their ratios. Quantitative and ordinal data were employed. These include tables and figures.

### **Results and discussions**

It was found out from interview conducted that Building and Road Research Institute (BRRI) has conducted research on burnt brick, adobe, wood, stabilised earth brick and rammed earth and all the research products been implemented across the country with the exception of bamboo and cast earth. The institute has future plans to further develop on earth/stabilised earth bricks and it is

considered to be marketable in terms of flexibility, adaptability and durability. BRRI has developed pozzollana as a new material/product in the last fifteen years which has successfully been introduced. It also considered cost of imported components and inflation as some of the factors that contribute to high cost of building materials. High cost of timber and taste for new products/prestige are the factors that force home developers to change to alternatives? Delays in acquiring for funds/payments form part of the difficulties in execution of construction projects. Insufficient on-site-supervision and construction management as well as land litigation contribute to construction constraint (personal communication, Mar, 2008).Estate developers were of the view that the government tenders for low-cost housing projects, specify expensive conventional building materials and technologies, instead of proven low-cost technologies developed by the government research institution. Training was identified as one of the key factors for the success of self-help building and cost of building materials was the main factor which prevents people to have access to domestic dwellings. Local research and development institutions have been able to disseminate information on new technology but no information about their supply to the local producers is disseminated. This is solely the responsibility of government bodies. The government has not been able to provide essential industrial extension services to feasibility studies, access to credit, import of equipment, or give training to domestic building materials industries. Lack of acquisition and documentation, clear procedures for building permits and certification, clear procedures for physical development and on the other hand, inflation on capital do not permit savings and thus, enhance haphazard physical development were found to be the impediment to the development of new building g materials /products(personal communication,Mar,2008).

## **Laboratory results**

### **Silt Content of Sand**

The result of the silt test conducted on the sand sample from the cylinder test showed that the sand contained an amount of 17.97% of silt, whilst the laterite contained an amount of 6.77% of silt.

The grading test performed on the sand sample (Table 1) indicates that 95.08% passed through the 5.00mm sieve and hence the sand sample could be classified as fine sand since the percentage passing through the sieve size 5.00mm was more than 50% (Neville,1995).

**Table 1 Grading Tests on Sand Sample of weight = 2789g.**  
**Time lapsed = 5minutes Amplitude = 8 (Intensity of vibration)**

B.S. Sieve	Wt.Retained	% Retained	% Passing	Riffled Wt.
6.30mm		0	100	100
5.00mm	137	4.92	95.08	95
4.75mm	8	0.29	94.79	95
2.36mm	146	5.25	89.54	90
1.18mm	599	21.52	68.02	68
600µm	1142	41.03	26.99	27
300µm	537	19.30	7.69	8
150µm	168	6.04	1.65	2
63µm(200mesh)	38	1.37	0.28	0.3
Receiving pan	8	0.28	0	0
Total	2783			

Source: Field Survey, 2011.

Furthermore, the percentage retained on the receiving pan was 0.28, which indicates that the amount of silt/clay in the sand was 0.28% ( Table 1).Thus the sample contained a low amount of silt/clay particles, which conforms to a value of 16% maximum, required in sand for block or concrete production (Neville, 1995).Again that silt content (receiving pan) of 0.28% shows that the result obtained from the grading test (Table 3) was far lower than that obtained from the cylinder test which recorded a value of 18% as the later is an approximate method.

### **Silt Content of Laterite**

The percentage retained on the receiving pan was 1.18%, which indicates that the amount of silt/clay in the laterite was 1.18%.Thus the sample contained a low amount of silt/clay particles

which conforms to a value of 16% maximum required in laterite for block or concrete production (Neville, 1995). Again, this silt content value of 1.18% shows that the result obtained from the grading test was far lower than that obtained from the cylinder test which records a value of 7% as the later was an approximate method. The result of grading test performs on both laterite and sand samples were summarized in tables 1 and 2 and presented in figures 1 and 2 respectively.

Table 2 Grading Tests on Laterite Sample of weight = 1367g  
Time lapsed = 5minutes Amplitude = 8 (Intensity of vibration)

<b>B.S. Sieve</b>	<b>Wt.Retained</b>	<b>% Retained</b>	<b>% Passing</b>	<b>Riffled Wt.</b>
20.00mm		0	100	100
14.00mm	16	1.18	98.82	99
9.50mm	109	8.05	90.77	91
6.30mm	241	17.80	72.97	73
5.00mm	146	10.78	62.19	62
4.75mm	48	3.55	58.64	59
2.36mm	387	28.58	30.06	30
1.18mm	193	14.25	15.81	16
600um	76	5.61	10.20	10
300um	51	3.77	6.43	6
150um	41	3.03	3.40	3
63um(200mesh)	30	2.22	1.18	1
Receiving pan	16	1.18	0	0
Total	1354			

Source: Field Survey, 2011.

## Grading Test on Laterite

The grading curve of a soil sample indicates whether particle distribution of a given sample is too fine or deficient in a particular size. The grading test performed on the laterite sample indicates that the dry laterite sample constituted 41.36% gravels (i.e. those that were retained on the BS 20mm sieve- to the 4.75mm sieve), 57.46% of sand (those that were retained on the BS 2.36mm sieve to the 63 micron sieve) and the fine particles in the laterite constitute 1.18% of Silt/clay (that was those retained on the receiving pan). This was further portrayed in figure 1, which shows the trend in which the particle size distribution occurred for the laterite sample. The figure shows that the laterite was uniformly graded material. Its silt/clay content of values 1.18% (dry laterite) and 6.77% (wet laterite ) proves that the silt was very low compared to the allowable value of 16% and may impact positively on the strength of the blocks that may be produced using the laterite sample alone as stated by (Neville,1995).

The graph shows that the Laterite was uniformly graded material. The 57.46% of the material that passed through the 4.75mm sieve and was retained on the 63 micron sieve indicates that the Laterite sample could be classified as sandy since more than 50% of it passed through the 4.75mm sieve (Table 2). According to (Neville, 1995), the uniformity of a soil (sand) was expressed qualitatively by a term known as uniformity co-efficient,  $C_u$ .

From the particle size distribution curve in the figure 1 for laterite,  $C_u = 8.08$ . This means, the Laterite was well-graded.

In figure 2 for sand  $C_u$  was found to be 3.21, which means the sand was not well-graded.




Figure 1 Grading Curve of Laterite (Source: Field Survey, 2011)



## GRADING CURVE OF SAND (PARTICLE SIZE DISTRIBUTION CURVE) PARTICLE SIZE (mm)




Figure 2 Grading Curve of Sand (Source: Field Survey, 2011)

### Compressive Strength of Laterite & Cement Blocks

The results of the seven-day and twenty-eight-day compressive strength tests performed on the various laterite and cement samples (landcrete Blocks) were tabulated in tables 3 and 4. Also the density of the blocks from each of the mix ratios were estimated from the weight and volume of each of the blocks samples and recorded. The results showed that, for the seven-day compressive strength test, the laterite and cement blocks recorded a compressive strength of 0.20 N/mm<sup>2</sup> for the ratio 1:6, 0.22 N/mm<sup>2</sup> for the ratio 1:8, 0.27 N/mm<sup>2</sup> for the ratio 1:10 and 0.76 N/mm<sup>2</sup> for the sandcrete block. Furthermore, the 28-day compressive strength test results showed that, the laterite & cement blocks recorded the values of 0.27N/mm<sup>2</sup> for the ratio 1:6, 0.39 N/mm<sup>2</sup> for the ratio 1:8, 0.49N/mm<sup>2</sup> for the ratio 1:10 and 1.14 N/mm<sup>2</sup> for the sandcrete blocks. This further implies that the sandcrete blocks are more durable than their landcrete blocks counterparts since a higher compressive strength indicates a higher durability property (Kerali, 2001).

### Density of Blocks

The average densities of all the mix ratios were found to be different even though, they had different strength values (Tables 3 and 4). These different in densities and strengths may be explained by the different in the particles size distribution of the different mixers.

## **Permeability of Blocks**

The results of the seven-day and twenty-eight-day absorption tests performed on the various laterite and cement samples (landcrete Blocks) and sandcrete blocks were tabulated in tables 5 and 6. This test was conducted to determine the level of water absorption of landcrete and sandcrete blocks. The results showed that, on the seventh day test for the landcrete blocks, the sample with ratio 1:6 recorded permeability of 21.07%, ratio 1:8 recorded 26.00% and ratio 1:10 recorded 13.81%. Ratio 1:10, which recorded the highest strength among the landcrete blocks also recorded the minimum water absorption. Also, the sandcrete blocks recorded water absorption level of 11.87%. This is just below the value recorded for the 1:10 landcrete block. This means that the sandcrete blocks were more durable than the 1:6, 1:8 and 1:10 landcrete blocks which recorded higher permeability. Furthermore, the 28-day water absorption test results showed that, the laterite & cement blocks recorded permeability of 10.30% for the ratio 1:6, 10.25% for the ratio 1:8, 11.39% for the ratio 1:10. Ratio 1:10, which recorded the highest strength among the landcrete blocks also recorded the highest water absorption. Also, the sandcrete blocks recorded water absorption level of 9.35%. This is just below the value recorded for the 1:8 landcrete block. This further implies that the sandcrete blocks are more durable than the 1:6, 1:8 and 1:10 landcrete blocks which recorded higher permeability.

## **Porosity of Blocks**

This test was conducted to determine the amount of pores in the landcrete and sandcrete blocks. The results of the seven-day and twenty-eight-day porosity tests performed on the various laterite and cement samples (landcrete Blocks) and sandcrete blocks were tabulated in tables 3 and 4. The results showed that, on the seventh day test for the landcrete blocks, the sample with ratio 1:6 recorded porosity of 32%, ratio 1:8 recorded 41% and ratio 1:10 recorded 22%. Ratio 1:10, which recorded the highest strength among the landcrete blocks also recorded the minimum porosity. Also, the sandcrete blocks recorded a porosity of 22%. The same value recorded for the 1:10 landcrete block. This means that the sandcrete blocks were only more durable than the 1:6 and 1:8 landcrete blocks which recorded higher porosity. The 28-day results showed that, the laterite and cement blocks recorded the values of 14% for the ratio 1:6, 16% for the ratio 1:8,

18% for the ratio 1:10 and 17% for the sandcrete blocks. This further implies that the sandcrete blocks were only more durable than the 1:10 landcrete blocks which recorded higher porosity.

## **Recommendations**

The following recommendations were given on the bases of the results of the study:

1. In forming landcrete blocks, special attention should be paid to the selection of the laterite and sand materials, as well as the sizes of the block.
2. More investigations should be carried out with a larger scope than was used in the study to confirm some of the finding as reported.
3. Other factors which are known to influence durability such as chemical attacks should be carried out in the future to find out their level of influence against durability of the blocks.
4. Government should: specify and tender for proven low-cost technologies developed by the government research institutions for its projects to help disseminate information on the new technology, establish training centers for individuals in the area of proven low-cost technologies to be self sufficient in the self-help building and be able to provide essential industrial extension services to feasibility studies, access to credit, import of equipment, or give training to domestic building materials industries.
5. There should be proper acquisition and documentation, clear procedures for building permits and certification, clear procedures for physical development.

## **Conclusions**

It was concluded that sandcrete blocks were more durable than landcrete blocks:

1. Since higher compressive strength values were recorded using the same cement content.
2. In terms of permeability, landcrete blocks recorded higher water absorption.
3. In terms of porosity, with cement: laterite ratio of 1:10.

It was also learnt that residential building industries have stopped using earth material for construction but this does not prevent them from accepting the new building technology if introduced into the market.

## **References**

Andam.A.K. (2004).Bricks, blocks and the future administrative capital of Ghana. A report delivered during the Inaugural

lecture of the Ghana Academy of Arts and Sciences,  
Dorcas.D. (2006). Salancrete Building Blocks from a Mixture of Sand, Laterite and Cement, Unpublished HND Project work.

Sunyani Polytechnic

Fales.F.J. (1991). Construction Technology Today and Tomorrow, Glenwe/M.C. Graw Hill, Peoria, IL 61614-1083.

Government of Ghana (2000): In J.O. Arumala, & L.L. Copeland (eds.) Affordable Housing in Developing Countries-The UMES Experience in

Ghana. Retrieved from <http://www.ascproceedings.org>. on July 6, 2007

Gidigasu.M.D. (2005). Lateritic soil construction for housing in Ghana, Journal of the Ghana Institution of Engineers, vol 3 number 2.

Gooding, D.E and Thomas, T.H. (1995). The potential of cement- stabilized building blocks as an urban building material in

the developing countries, DTU working paper No.44.

Government of Ghana (2000): In J.O. Arumala, & L.L. Copeland (eds.)

Affordable Housing in Developing Countries-The UMES Experience in

Ghana. Retrieved from <http://www.ascproceedings.org> on July 6, 2007

Karima, (1998): In CHF International,(2004), Strategic Assessment of the Affordable Housing Sector in Ghana.

Retrieved from <http://www.chfhq.com/files/1428-file-Ghana-Housing.report.pdf> on July 5, 2005

Karl, (2000): In, S.K. Paudel, Bamboo Housing, INBAR Economic Development Programme. Retrieved from on <http://www.inbar.int/housing/introduction.htm> on January 31, 2005 from

Neville, A.M. (1995). Properties of Concrete (4th Ed). Essex CM20 2JE, England: Pearson Education Limited Retrieved from [www.theghanaijournal.com](http://www.theghanaijournal.com) on March 14, 2011

Patara, S. (1998), Promotion of innovation Building Materials, Sustainable Livelihoods. Retrieved from <http://www.dainet.org/livelihoods/0198p.htm>. on February 1, 2006.

Statesman (2007), A brief history of housing in Ghana, General News. Retrieved

from <http://www.ghanaweb.com/GhanaHomePage/NewsArchive/artikel.php?ID=18043> on January 12, 2011.

UNCHS, (1991) Technology in human settlements, Nairobi.